MIFAST DISPERMID PA - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
Y.14	DISAZO	YELLOW	PA 2011/55	50%	50%	0%	4	5	4	4-5	5	5
Y.74	MONOAZO	YELLOW	PA 2032/50	50%	50%	0%	7	5	5	4	5	5
Y.83	DISAZO	YELLOW	PA 2013/55	55%	45%	0%	6-7	5	5	5	5	5
O.34	PYRAZOLONE ORANGE	ORANGE	PA 4034/60	45%	55%	0%	7	4	5	3	5	5
O.46	LAKE ORANGE B	ORANGE	PA 4016/55	55%	45%	0%	4-5	5	5	3	4-5	2
R.48:2	2B TONER CALCIUM	RED	PA 5012/55	55%	45%	0%	5	4-5	4	5	3	5
R.53:1	LAKE RED C	RED	PA 5018/55	50%	48%	2%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	PA 5023/55	55%	44%	1%	3	3	3	4-5	2	3
R.122	QUINACRIDONE	PINK	PA 5005/50	50%	50%	0%	7	5	5	5	5	5
R.166	AZO CONDENSATION	RED	PA 5166/55	50%	48%	2%	7-8	5	5	5	5	5
V.23	DIOXAZINE VIOLET	VIOLET	PA 7010/55	50%	50%	0%	8	5	5	5	4	5
B.15:3	PHTHALO	BLUE	PA 6010/55	50%	48%	2%	8	5	5	5	5	5
B.15:4	PHTHALO	BLUE	PA 6030/55	55%	45%	0%	8	5	5	5	5	5
B.27	MILORI BLUE	BLUE	PA 6027/65	65%	35%	0%	8	5	5	5	2	5
G.7	PHTHALO	GREEN	PA 9010/55	55%	45%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	PA 3000/50	50%	48%	2%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.