MIFAST DISPERCAP AP - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	AP 8000/80	75%	21%	4%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	AP 2413/60	60%	37%	3%	5	5	5	4	5	4
Y.83	DISAZO	YELLOW	AP 2083/60	55%	42%	3%	6-7	5	5	5	5	5
R.48:1	2B TONER BARIUM	RED	AP 5481/60	55%	45%	0%	4	4	4	4	4	5
R.48:2	2B TONER CALCIUM	RED	AP 5482/60	55%	45%	0%	5	4-5	4	5	3	5
R.53:1	LAKE RED C	RED	AP 5531/60	55%	42%	3%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	AP 5571/60	55%	42%	3%	3	3	3	4-5	2	2
R.184	NAPHTHOL AS	RED	AP 5184/60	50%	37%	13%	5-6	5	5	4-5	5	3-4
V.23	DIOXAZINE VIOLET	VIOLET	AP 7023/60	60%	37%	3%	8	5	5	5	4	5
B.15:3	PHTHALO	BLUE	AP 6153/60	60%	37%	3%	8	5	5	5	5	5
B.15:4	PHTHALO	BLUE	AP 6154/60	60%	30%	10%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	AP 9007/60	55%	42%	3%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	AP 9007/64	50%	40%	10%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	AP 3035/35	60%	37%	3%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	AP 3060/60	55%	42%	3%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.