MIFAST DISPERCAB CB - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	CB 8000/80	80%	17%	3%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	CB 2413/50	50%	40%	10%	5	5	5	4	5	4
Y.83	DISAZO	YELLOW	CB 2083/50	50%	40%	10%	6-7	5	5	5	5	5
Y.155	DISAZO	YELLOW	CB 2035/50	45%	45%	10%	7	5	5	4-5	5	5
O.34	PYRAZOLONE ORANGE	ORANGE	CB 4034/50	40%	49%	11%	7	4	5	3	5	5
R.48:2	2B TONER CALCIUM	RED	CB 5482/50	45%	44%	11%	5	4-5	4	5	3	5
R.53:1	LAKE RED C	RED	CB 5531/50	50%	40%	10%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	CB 5571/50	45%	44%	11%	3	3	3	4-5	2	3
R.122	QUINACRIDONE	PINK	CB 5122/50	50%	40%	10%	7	5	5	5	5	5
V.23	DIOXAZINE VIOLET	VIOLET	CB 7023/50	50%	40%	10%	8	5	5	5	4	5
B.15:3	PHTHALO	BLUE	CB 6153/50	50%	40%	10%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	CB 6153/60	60%	30%	10%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	CB 9007/50	50%	40%	10%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	CB 3007/40	45%	47%	8%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.