MIFAST DISPERCRYL AW - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	AW 8000/78	80%	20%	0%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	AW 2413/78	55%	45%	0%	5	5	5	4	5	4
Y.83	DISAZO	YELLOW	AW 2083/78	50%	50%	0%	6-7	5	5	5	5	5
R.49:1	MONOAZO	RED	AW 5491/78	50%	50%	0%	5	5	3	3	-	-
R.53:1	LAKE RED	RED	AW 5531/78	55%	45%	0%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	AW 5571/78	50%	50%	0%	3	3	3	4-5	2	3
R.166	AZO CONDENSATION	RED	AW 5066/78	55%	45%	0%	7-8	5	5	5	5	5
V.23	DIOXAZINE VIOLET	VIOLET	AW 7023/78	50%	50%	0%	8	5	5	5	4	5
B.15:3	PHTHALO	BLUE	AW 6153/78	55%	45%	0%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	AW 9007/78	55%	45%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	AW 3004/78	55%	45%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	AW 3804/78	45%	55%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	AW 3804/50	45%	55%	0%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.