MIFAST DISPERVYN WB - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	WB 8000	80%	20%	0%	8	5	5	5	5	5
O.34	PYRAZZOLONE	ORANGE	WB 4034	55%	45%	0%	7	4	5	3	5	5
R.57:1	4B TONER CALCIUM	RED	WB 5571	60%	35%	5%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	WB 5572	55%	45%	0%	3	3	3	4-5	2	3
R.147	NAPHTHOL AS	RED	WB 5147	65%	35%	0%	5	5	5	4	5	5
R.254	DIKETO-PIRROLO-PYRROLE	RED	WB 5254	45%	55%	0%	8	5	5	5	5	5
V.23	DIOXAZINE VIOLET	VIOLET	WB 7023	60%	40%	0%	8	5	5	5	4	5
V.37	DIOXAZINE VIOLET	VIOLET	WB 7037	60%	35%	5%	7	5	5	4-5	5	5
B.15:3	PHTHALO	BLUE	WB 6153	65%	30%	5%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	WB 6153/70	70%	25%	5%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	WB 9707	55%	45%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	WB 3007	50%	50%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	WB 3804/54	50%	50%	0%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.