DISPERCOS - PRODUCT RANGE

COLOR INDEX	PIGMENT COLOR LABELLING	COLOR	NAME	CODE	Pigment C.A.S. Number	COMPOSITION			STANDARD SPECIFICATION					
						Pigment	NC	ATBC	Lightfastness[1]	Chemical resistance[2]				
										Alkali	Acids	Solvents	Soap	Butter
W.OX	TITANIUM DIOXIDE	WHITE	DISPERCOS WHITE TITANIUM DIOXIDE	COS 800001	13463-67-7	75%	15%	10%	8	5	5	5	5	5
W.6	TITANIUM DIOXIDE	WHITE	DISPERCOS POLY WHITE	COS 800002	not applicable	75%	15%	10%	8	5	5	5	5	5
W.6	TITANIUM DIOXIDE	WHITE	DISPERCOS POLY WHITE TRAITE	COS 800003	not applicable	75%	15%	10%	8	5	5	5	5	5
Y.100	SULFONIC ACID	YELLOW	DISPERCOS YELLOW No 5	COS 200501	12225-21-7	40%	45%	15%	2	2	2	2	-	-
Y.6	SULFONIC ACID	YELLOW	DISPERCOS YELLOW No 6	COS 200601	15790-07-5	40%	45%	15%	2	2	2	2	-	-
Y.115	SULFONIC ACID	YELLOW	DISPERCOS YELLOW No 10	COS 201001	68814-04-0	40%	45%	15%	3	4	3	3	-	-
F.Y.17	ALUMINIUM HYDROXIDE	YELLOW	DISPERCOS FLUORESCENT YELLOW Nø 17	COS 261750	21654-51-2	50%	35%	15%	2	2	2	2	-	-
R.27	FLUORAN	RED	DISPERCOS RED No 27	COS 500027	13743-26-2	40%	45%	15%	2	2	2	2	-	-
R.6	BARIUM HYDROXIDE	RED	DISPERCOS RED No 6	COS 500601	17852-98-1	40%	43%	17%	4	3	2	4	-	-
R.57:1	4B TONER CALCIUM	RED	DISPERCOS RED No 7 LIGHT	COS 500701	5281-04-09	40%	45%	15%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	DISPERCOS RED No 7 DARK	COS 500702	5281-04-09	40%	45%	15%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	DISPERCOS RED 7 - KF	COS 500703	5281-04-09	30%	54%	16%	3	3	3	4-5	2	3
R.63:1	MONO AZO	RED	DISPERCOS RED No 34	COS 503401	6417-83-0	40%	45%	15%	4	3	3	4	-	-
R.4	B-NAPHTHOL	RED	DISPERCOS RED No 36	COS 503601	2817-77-9	40%	45%	15%	4	5	5	4	5	3-4
V.16	MANGANESE VIOLET	VIOLET	DISPERCOS VIOLET No.16	COS 701601	10101-66-3	40%	45%	15%	5	2	5	5	-	-
B.2C	ALUMINIUM SALT	BLUE	DISPERCOS BLUE No 1	COS 600101	272-939-6	40%	45%	15%	2	2	2	2	-	-
Blu UltraMarine	DIALUMINIUM SALT	BLUE	DISPERCOS BLUE ULTRAMARINE	COS 603940	15792-67-3	40%	45%	15%	8	5	2	5	-	-
B.27	MILORI BLUE	BLUE	DISPERCOS CROMA IRON BLUE	COS 650101	25869-00-5	50%	40%	10%	8	5	5	5	5	5
Bl.2	CARBON BLACK	BLACK	DISPERCOS BLACK 2	COS 350201	215-609-9	20%	55%	25%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.