DISPERLIT VK - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	VK8000	75%	22%	3%	8	5	5	5	5	5
Y.83	DISAZO	YELLOW	VK2083	45%	52%	3%	6-7	5	5	5	5	5
Y.93	DOUBLE AZO	YELLOW	VK2093	45%	53%	2%	7	5	5	5	5	5
Y.110	ISODIOLINO	YELLOW	VK2110	50%	48%	2%	8	5	5	3-4	-	-
R.144	AZO CONDENSATION	RED	VK5144	40%	60%	0%	7-8	5	5	5	5	5
R.144	AZO CONDENSATION	RED	VK5144HT	40%	60%	0%	7-8	5	5	5	5	5
R.185	BENZIMIDAZOLONE	RED	VK5185	45%	51%	4%	7-8	5	5	5	5	5
R.202	QUINACRIDONE	RED	VK5202	50%	46%	4%	7	5	5	4-5	5	5
R.254	DIKETO-PIRROLO-PYRROLE	RED	VK5254	45%	55%	0%	8	5	5	5	5	5
R.254	DIKETO-PIRROLO-PYRROLE	RED	VK5254HT	45%	53%	2%	8	5	5	5	5	5
V.37	DIOXANINE VIOLET	VIOLET	VK7037	45%	52%	3%	7	5	5	4-5	5	5
B.60	INDANTHRONE	BLUE	VK6060T	50%	44%	6%	8	5	5	3	-	-
B.15:3	PHTHALO	BLUE	VK6153	50%	46%	4%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	VK9007	45%	53%	2%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VK3007	45%	49%	6%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.