MIFAST DISPERVYN VD - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	VD 8000/20	75%	22%	3%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	VD 2012/50	50%	49%	1%	5	5	5	4	5	4
Y.14	DISAZO	YELLOW	VD 2011/20	55%	43%	2%	4	5	4	4-5	5	5
Y.17	DISAZO	YELLOW	VD 2010/20	55%	44%	1%	6	5	5	4-5	5	5
Y.17	DISAZO	YELLOW	VD 2017/10	55%	44%	1%	6	5	5	4-5	5	5
Y.83	DISAZO	YELLOW	VD 2013/20	50%	47%	3%	6-7	5	5	5	5	5
Y.83	DISAZO	YELLOW	VD 2013/21	45%	54%	1%	6-7	5	5	5	5	5
Y.83	DISAZO	YELLOW	VD 2083/10	45%	54%	1%	6-7	5	5	5	5	5
O.34	PYRAZOLONE	ORANGE	VD 4012/20	55%	44%	1%	7	4	5	3	5	5
R.48:1	2B TONER BARIUM	RED	VD 5011/20	55%	44%	1%	4	4	4	4	4	5
R.48:1	2B TONER BARIUM	RED	VD 5481/55	55%	44%	1%	4	4	4	4	4	5
R.48:2	2B TONER CALCIUM	RED	VD 5012/10	55%	44%	1%	5	4-5	4	5	3	5
R.48:2	2B TONER CALCIUM	RED	VD 5012/20	55%	44%	1%	5	4-5	4	5	3	5
R.57:1	4B TONER CALCIUM	RED	VD 5023/20	50%	47%	3%	3	3	3	4-5	2	5
R.122	QUINACRIDONE	PINK	VD 5005/02	50%	50%	0%	7	5	5	5	5	5
R.122	QUINACRIDONE	PINK	VD 5005/20	50%	50%	0%	7	5	5	5	5	5
R.146	NAPHTHOL AS	RED	VD 5033/21	55%	44%	1%	5-6	5	5	4-5	4	4-5
R.147	NAPHTHOL AS	RED	VD 5034/00	55%	44%	1%	5	5	5	4	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.

MIFAST DISPERVYN VD - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
R.166	AZO CONDENSATION	RED	VD 5048/00	50%	48%	2%	7-8	5	5	5	5	5
R.210	NAPHTHOL AS	RED	VD 5021/00	55%	45%	0%	7	5	5	4	4	4
V.23	DIOXAZINE VIOLET	VIOLET	VD 7023/20	55%	43%	2%	8	5	5	5	4	5
V.32	AZO CONDENSATION	VIOLET	VD 5035/01	55%	43%	2%	6	5	5	5	5	5
B.15:3	PHTHALO	BLUE	VD 6015/20	55%	41%	4%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	VD 9010/20	55%	43%	2%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VD 3000/20	45%	53%	2%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VD 3000/21	45%	51%	4%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VD 3045/10	40%	57%	3%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.