MIFAST DISPERVYN VI - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	VI 8000/15	75%	22%	3%	8	5	5	5	5	5
W.6	TITANIUM DIOXIDE	WHITE	VI 8000/15 M	75%	22%	3%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	VI 2413/15	50%	47%	3%	5	5	5	4	5	4
Y.14	DISAZO	YELLOW	VI 2011/15	50%	46%	4%	4	5	4	4-5	5	5
Y.17	DISAZO	YELLOW	VI 2010/15	50%	47%	3%	6	5	5	4-5	5	5
Y.17	DISAZO	YELLOW	VI 2010/15 M	50%	47%	3%	6	5	5	4-5	5	5
Y.17	DISAZO	YELLOW	VI 2017/15	50%	47%	3%	6	5	5	4-5	5	5
Y.83	DISAZO	YELLOW	VI 2013/15	50%	47%	3%	6-7	5	5	5	5	5
Y.83	DISAZO	YELLOW	VI 2013/15 M	50%	47%	3%	6-7	5	5	5	5	5
Y.83	DISAZO	YELLOW	VI 2083/70 M	50%	47%	3%	6-7	5	5	5	5	5
Y.155	DISAZO	YELLOW	VI 2155/15	50%	49%	1%	7	5	5	4-5	5	5
Y.42	IRON OXIDE HYDRATE	YELLOW	VI 2442/15	70%	27%	3%	8	5	5	5	5	5
O.5	DINITRANILINE	ORANGE	VI 4005/15	55%	43%	2%	6-7	5	5	4	5	3
O.5	DINITRANILINE	ORANGE	VI 4010/15 M	50%	46%	4%	6-7	5	5	4	5	3
O.34	PYRAZOLONE	ORANGE	VI 4012/15	50%	46%	4%	7	4	5	3	5	5
O.38	NAPHTHOL AS	ORANGE	VI 4038/15	50%	50%	0%	6	5	5	5	5	5
R.48:2	2B TONER CALCIUM	RED	VI 5012/15	50%	47%	3%	5	4-5	4	5	3	5
R.48:4	2B TONER MANGANESE	RED	VI 5015/15 M	50%	47%	3%	7	4	4-5	5	3-4	4-5
R.53:1	LAKE RED	RED	VI 5010/15	50%	48%	2%	3	3	3	4-5	2	3
R.57:1	2B TONER CALCIUM	RED	VI 5023/15	50%	48%	2%	3	3	3	4-5	2	3
R.57:1	2B TONER CALCIUM	RED	VI 5023/15 M	50%	48%	2%	3	3	3	4-5	2	3
R.122	QUINACRIDONE	PINK	VI 5005/15	50%	47%	3%	7	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.

MIFAST DISPERVYN VI - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
R.122	QUINACRIDONE	PINK	VI 5005/15 M	50%	47%	3%	7	5	5	5	5	5
R.144	AZO CONDENSATION	RED	VI 5044/15	50%	48%	2%	7-8	5	5	5	5	5
R.146	NAPHTHOL AS	RED	VI 5033/25	55%	42%	3%	5-6	5	5	4-5	4	4-5
R.147	NAPHTHOL AS	RED	VI 5034/15	50%	48%	2%	5	5	5	4	5	5
R.166	AZO CONDENSATION	RED	VI 5048/15	45%	53%	2%	7-8	5	5	5	5	5
R.166	AZO CONDENSATION	RED	VI 5048/15 M	45%	53%	2%	7-8	5	5	5	5	5
R.166	AZO CONDENSATION	RED	VI 5066/15	45%	53%	2%	7-8	5	5	5	5	5
R.170	NAPHTHOL AS	RED	VI 5170/15	50%	46%	4%	5	5	5	4-5	-	-
R.184	NAPHTHOL AS	RED	VI 5049/15	50%	47%	3%	5-6	5	5	4-5	5	3-4
R.185	NBON-ARYLAMIDE BENZIM.	RED	VI 5078/15	50%	48%	2%	7-8	5	5	5	5	5
R.101	IRON III OXIDE	RED	VI 5401/15	70%	27%	3%	8	5	5	5	5	5
V.23	DIOXAZINE VIOLET	VIOLET	VI 7010/15	50%	48%	2%	5	5	5	5	3	4
V.23	DIOXAZINE VIOLET	VIOLET	VI 7010/15 M	50%	48%	2%	8	5	5	5	4	5
B.15:3	PHTHALO	BLUE	VI 6010/15	50%	47%	3%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	VI 6010/15 M	50%	47%	3%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	VI 6030/15	50%	47%	3%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	VI 9010/15	55%	43%	2%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VI 3000/15	45%	53%	2%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VI 3000/15 M	45%	53%	2%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VI 3000/45	45%	51%	4%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VI 3807/15	45%	49%	6%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.