MIFAST DISPERVYN VB - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	VB 8000/80	80%	20%	0%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	VB 2413/61	60%	40%	0%	5	5	5	4	5	4
Y.13	DISAZO	YELLOW	VB 2413/70	70%	30%	0%	5	5	5	4	5	4
Y.14	DISAZO	YELLOW	VB 2014/65	65%	35%	0%	4	5	4	4-5	5	5
Y.14	DISAZO	YELLOW	VB 2714/65	65%	30%	5%	4	5	4	4-5	5	5
Y.17	DISAZO	YELLOW	VB 2017/65	65%	35%	0%	6	5	5	4-5	5	5
Y.83	DISAZO	YELLOW	VB 2083/65	65%	35%	0%	6-7	5	5	5	5	5
Y.155	DISAZO	YELLOW	VB 2155/50	50%	50%	0%	7	5	5	4-5	5	5
O.34	PYRAZOLONE	ORANGE	VB 4034/65	65%	35%	0%	7	4	5	3	5	5
R.48:2	2B TONER CALCIUM	RED	VB 5482/60	60%	40%	0%	5	4-5	4	5	3	5
R.57:1	4B TONER CALCIUM	RED	VB 5572	55%	45%	0%	3	3	3	4-5	2	3
R.57:1	4B TONER CALCIUM	RED	VB 5571/60	55%	45%	0%	3	3	3	4-5	2	3
R.122	QUINACRIDONE	PINK	VB 5122/50	50%	50%	0%	7	5	5	5	5	5
R.146	NAPHTHOL AS	RED	VB 5146/60	60%	40%	0%	5-6	5	5	4-5	4	4-5
R.147	NAPHTHOL AS	RED	VB 5034/65	65%	35%	0%	5	5	5	4	5	5
R.170	NAPHTHOL AS	RED	VB 5170/70	70%	30%	0%	5	5	5	4-5	-	-
R.184	NAPHTHOL AS	RED	VB 5184/51	50%	50%	0%	5-6	5	5	4-5	5	3-4
R.184	NAPHTHOL AS	RED	VB 5184/65	65%	35%	0%	5-6	5	5	4-5	5	3-4

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.

MIFAST DISPERVYN VB - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
R.254	DIKETO-PIRROLO-PYRROLE	RED	VB 5254/60	60%	40%	0%	8	5	5	5	5	5
V.23	DIOXAZINE VIOLET	VIOLET	VB 7023/60	60%	40%	0%	8	5	5	5	4	5
V.37	DIOXAZINE VIOLET	VIOLET	VB 7037/65	60%	35%	5%	7	5	5	4-5	5	5
B.15:3	PHTHALO	BLUE	VB 6153/60	60%	40%	0%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	VB 6153/62	60%	40%	0%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	VB 6153/70	70%	25%	5%	8	5	5	5	5	5
B.15:3	PHTHALO	BLUE	VB 6153/71	70%	30%	0%	8	5	5	5	5	5
B.15:4	PHTHALO	BLUE	VB 6154/60	55%	45%	0%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	VB 9707/60	55%	45%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VB 3000/60	60%	40%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VB 3002/60	60%	40%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VB 3007/54	50%	44%	6%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VB 3007/60	60%	40%	0%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	VB 3060/50	50%	50%	0%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.