MIFAST DISPERTHYL EC - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	EC 8000	70%	27%	3%	8	5	5	5	5	5
Y.13	DISAZO	YELLOW	EC 2413	50%	45%	5%	5	5	5	4	5	4
Y.83	DISAZO	YELLOW	EC 2023	50%	45%	5%	6-7	5	5	5	5	5
R.48:2	2B TONER CALCIUM	RED	EC 5012	50%	45%	5%	5	4-5	4	5	3	5
R.146	NAPHTHOL AS	RED	EC 5033	50%	45%	5%	5-6	5	5	4-5	4	4-5
R.166	AZO CONDENSATION	RED	EC 5048OP	50%	45%	5%	7-8	5	5	5	5	5
R.166	AZO CONDENSATION	RED	EC 5166HT	50%	45%	5%	7-8	5	5	5	5	5
Br. 23	AZO CONDENSATION	BROWN	EC 5123	50%	45%	5%	6-7	3-4	-	4-5	-	-
B.15:3	PHTHALO	BLUE	EC 6010	50%	45%	5%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	EC 9010	50%	45%	5%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	EC 3000	50%	45%	5%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.