DISPERLIT EC - PRODUCT RANGE

COLOR INDEX	PIGMENT CLASS	COLOR	CODE	COMPOSITION			STANDARD SPECIFICATION					
				% Pigment	% Resin	% Plasticizer	Lightfastness[1]	Chemical resistance[2]				
								Alkali	Acids	Solvents	Soap	Butter
W.6	TITANIUM DIOXIDE	WHITE	EC 8000 M	70%	27%	3%	8	5	5	5	5	5
Y.83	DISAZO	YELLOW	EC 2023 M	50%	45%	5%	6-7	5	5	5	5	5
Y.83	DISAZO	YELLOW	EC 2083 NO	50%	45%	5%	6-7	5	5	5	5	5
Y.93	DISAZO	YELLOW	EC 2193 M	50%	45%	5%	7	5	5	5	5	5
Y.13	DISAZO	YELLOW	EC 2413 M	50%	45%	5%	5	5	5	4	5	4
O.34	PYRAZOLONE ORANGE	ORANGE	EC 4034 NO	50%	45%	5%	7	4	5	3	5	5
R.48:2	2B TONER CALCIUM	RED	EC 5012 M	50%	45%	5%	5	4-5	4	5	3	5
R.146	NAPHTHOL AS	RED	EC 5033 M	50%	45%	5%	5-6	5	5	4-5	4	4-5
R.166	AZO CONDENSATION	RED	EC 5048O PM	50%	45%	5%	7-8	5	5	5	5	5
R.184	NAPHTHOL AS	RED	EC 5049 M	50%	45%	5%	5-6	5	5	4-5	5	3-4
Br.23	AZO CONDENSATION	#N/D	EC 5123 M	50%	45%	5%	6-7	3-4	-	4-5	-	-
R.166	AZO CONDENSATION	RED	EC 5166 HTM	50%	45%	5%	7-8	5	5	5	5	5
V.37	DIOXAZINE VIOLET	VIOLET	EC 7037 M	50%	45%	5%	7	5	5	4-5	5	5
B.15:3	PHTHALO	BLUE	EC 6010 M	50%	45%	5%	8	5	5	5	5	5
G.7	PHTHALO	GREEN	EC 9010 M	50%	45%	5%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	EC 3000 M	50%	45%	5%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	EC 3000 MHO	55%	35%	10%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	EC 3000 MNT	55%	40%	5%	8	5	5	5	5	5
Bl.7	CARBON BLACK	BLACK	EC 3070 M	70%	26%	4%	8	5	5	5	5	5

Dispersions and colours can be supplied either from standard ranges or, through development and application testing, as bespoke products designed for individual customers.

Colours are representation only and are in no way intended to convey the shade of the actual colour and shade.
If not otherwise stated, all NC products are ATBC plasticized.
1 – Blue Wool Scale, 1 – 8 (8 best)
2 – Measured on scale of 1 – 5 (5 best)
The information herewith given is based on our present knowledge. Any conclusion and recommendation are made without liability on our part. Buyers and users are advised to make their own assessment under their own condition and for their own requirements.